



## **P.U. Zinc Rich Primer**

### SCOPE

A two pack P.U. zinc pigmented blast primer which gives long term protection to freshly blast cleaned steel depending on the prevailing conditions it does not affect welding or cutting operations. It can be over coated with wide range of high performance coatings such as Epoxy, Polyurethane, H.R.Paint, Chlororubber etc. Inconjunction with system. With excellent weather resistance properties. It withstands back-filling materials and is not affected. It is specially develop for application smooth surfaces as SS, Galvanize, Aluminum etc.

### TECHNICAL DETAILS

Type : Two pack, cold cured.  
Mixing ratio : Base : Catalyst : 3.6 : 0.4 by volume.  
Pot Life : 1 hours.  
Allocation: Brush, Roller, Airless spray.  
Recommended DFT : 26-50 microns per coat.  
Corresponding WFT : 75-150 microns per coat.  
Theoretical Spreading Rate : 6.0 - 12 Sq. Mt/Lt.  
Drying Time : Touch Dry : 5-10 Min.  
: Dry to Handle: 1.30 Hours  
: Hard Dry: 4 hours.  
: Curing Time: 7 days.  
Overcoating Interval : 24 Hours.  
Thinner : 1-UP P.U. Thinner.  
Finish : Matt.  
Storage life : Upped nine months as long as they  
: Are kept under cover in dry place  
: Under normal temperature.

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND  
CUSTOMER IS ADVISED TO TEST THE MATERIAL BEFORE USE

KIRAN PAINTS PVT. LTD.

Factory : Plot No. 48, M.I.D.C., Taloja Ind. Area, Dist. Raigad, Maharashtra-410208, INDIA.

Fact. Tel.: 91-22-27410100 Fax: 91-22-27410101 Mobile: 9320724330

Email : [info@kiranpaints.com](mailto:info@kiranpaints.com)

Website : [www.kiranpaints.com](http://www.kiranpaints.com)